

SUBJECT

Evaluation of "Coconut Shell Charcoal Briquette for Barbeque" Sample for Self-Heating Substance Test

CLIENT

PT. Pandu Green Energi
Bellezza BSA 1st Floor SA1-06,
Jl. Letjen Soep Grogol Utara, Kebayoran Lama,
Kota ADM, Jakarta Selatan, DKI Jakarta

DATE OF RECEIVED SAMPLE

August 23th, 2022

DESCRIPTION OF SAMPLE

Coconut Shell Charcoal Briquette for Barbeque

DATE OF TESTING

August 23th Up To August 26th, 2022

The below findings are based on sample/s only, which is/are submitted or supplied by client. This report is valid within 90 days from the date of testing.



This report is made and issued by the Company upon the Principal/Applicant's request and the analysis contained therein reflects the Company's findings on the sample(s) submitted by Principal/Applicant and/or sample(s) drawn by the Company at the time and place of performing the inspection/testing only. Company shall not be liable for any changes to the results herein due to effects of weather, transport, storage or other factors outside Company's control. Furthermore, the Company shall not be responsible to any parties on any business, financial and/or legal consequences for any transaction by using this report/analysis. Any unauthorised alteration or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. This document cannot be reproduced except in full, without prior approval of the Company.

METHOD OF TEST

The self heating substances test was performed according to United Nations "Recommendations on the Transport Dangerous Good, Manual of Test and Criteria" (33.4.3.3.1) as per revised UN test manual 7th edition 2019. Self heating substances, using method of UN 33.4.6 "Test N.4: Test method self-heating substances".

A consignment of carbon if it passes the tests for self-heating substances as reflected in the United Nations Manual of Tests and Criteria (see 33.3.1.3.3), and is accompanied by a certificate from a laboratory accredited by the competent authority, stating that the product to be loaded has been correctly sampled by trained staff from that laboratory and that the sample was correctly tested and has passed the test.

The sample received was placed into was the placed into a 100 mm cubic mesh sample container made of stainless steel. The container was then hung at the centre of the oven. The oven temperature was slowly raised to 140o C and kept constant for 24 hours. The temperature at the centre of the sample and temperature between the container and oven were recorded continuously.

RESULT

Table 1: Analysis result for "Coconut Shell Charcoal Briquette for Barbeque" Sample


Sample	Oven Temperature (°C)	Cube Size (mm)	Maximum Temperature Reached (°C)	Result
Coconut Shell Charcoal Briquette for Barbeque	140	100	204.4	Positive
Coconut Shell Charcoal Briquette for Barbeque	140	25	140.7	Negative
Coconut Shell Charcoal Briquette for Barbeque	120	100	120.8	Negative

The above result showed that the "Coconut Shell Charcoal Briquette for Barbeque" sample shall not be classified in self heating substances and the substance is to be contained in packages of not more than 3 m3.

Remark


The temperature profiles were enclosed in next pages for your references. T1 represented temperature in the center of the sample. T2 represented temperature between the container and the oven wall.

Jakarta, August 31st, 2022
PT. CARSURIN



Dede Jemmi Supriadi
Head of Laboratory

PT. CARSURIN



CARSURIN
1968

Amran Lesmana
Head of Technical Charcoal

For verification of authenticity certificate or report, please e-mail to Charcoal@carsurin.com




This report is made and issued by the Company upon the Principal/Applicant's request and the analysis contained therein reflects the Company's findings on the sample(s) submitted by Principal/Applicant and/or sample(s) drawn by the Company at the time and place of performing the inspection/testing only. Company shall not be liable for any changes to the results herein due to effects of weather, transport, storage or other factors outside Company's control. Furthermore, the Company shall not be responsible to any parties on any business, financial and/or legal consequences for any transaction by using this report/analysis. Any unauthorised alteration or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. This document cannot be reproduced except in full, without prior approval of the Company.

The Temperature Profile "Coconut Shell Charcoal Briquette for Barbeque" at 140° C (100mm cube)

Start Time : August 24th, 2022 21:00:00
Stop Time : August 25th, 2022 02:00:00
Elapsed Time : 05:00:00
Interval : 0:30:00
Total readings : 11
Thermocouple Type : K
Scaling : (none)

	Max Time Stamp	Max	Average	Min	Min Time Stamp
T1	8/24/2022 2:00	204.4	147.2	133.8	8/23/2022 21:00
T2	8/24/2022 1:30	144.4	138.4	135.4	8/23/2022 21:00
T1-T2	8/24/2022 2:00	69.1	8.8	-10.6	8/23/2022 21:00



Remark:

T1 represented temperature in the centre of the sample. T2 represented temperature between the container and the oven wall.




This report is made and issued by the Company upon the Principal/Applicant's request and the analysis contained therein reflects the Company's findings on the sample(s) submitted by Principal/Applicant and/or sample(s) drawn by the Company at the time and place of performing the inspection/testing only. Company shall not be liable for any changes to the results herein due to effects of weather, transport, storage or other factors outside Company's control. Furthermore, the Company shall not be responsible to any parties on any business, financial and/or legal consequences for any transaction by using this report/analysis. Any unauthorised alteration or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. This document cannot be reproduced except in full, without prior approval of the Company.

24 Hours Temperature Profile "Coconut Shell Charcoal Briquette for Barbeque" at 140° C (25mm cube)

Start Time : August 24th, 2022 02:30:00
 Stop Time : August 25th, 2022 02:30:00
 Elapsed Time : 24:00:00
 Interval : 0:30:00
 Total readings : 49
 Thermocouple Type : K
 Scaling : (none)

	Max Time Stamp	Max	Average	Min	Min Time Stamp
T1	8/24/2022 13:30	140.7	139.9	120.0	8/24/2022 2:30
T2	8/24/2022 18:00	138.5	138.1	129.2	8/24/2022 2:30
T1-T2	8/25/2022 2:30	2.4	1.8	-9.1	8/24/2022 2:30



Remark:

T1 represented temperature in the centre of the sample. T2 represented temperature between the container and the oven wall.




This report is made and issued by the Company upon the Principal/Applicant's request and the analysis contained therein reflects the Company's findings on the sample(s) submitted by Principal/Applicant and/or sample(s) drawn by the Company at the time and place of performing the inspection/testing only. Company shall not be liable for any changes to the results herein due to effects of weather, transport, storage or other factors outside Company's control. Furthermore, the Company shall not be responsible to any parties on any business, financial and/or legal consequences for any transaction by using this report/analysis. Any unauthorised alteration or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. This document cannot be reproduced except in full, without prior approval of the Company.

24 Hours Temperature Profile "Coconut Shell Charcoal Briquette for Barbeque" at 120° C (100mm cube)

Start Time : August 25th, 2022 02:30:00
 Stop Time : August 26th, 2022 02:30:00
 Elapsed Time : 24:00:00
 Interval : 0:30:00
 Total readings : 49
 Thermocouple Type : K
 Scaling : (none)

	Max Time Stamp	Max	Average	Min	Min Time Stamp
T1	8/25/2022 6:30	120.8	120.5	113.0	8/25/2022 2:30
T2	8/25/2022 18:00	120.3	120.2	118.4	8/25/2022 2:30
T1-T2	8/25/2022 8:00	0.6	0.3	-5.4	8/25/2022 2:30



Remark:

T1 represented temperature in the centre of the sample. T2 represented temperature between the container and the oven wall.



This report is made and issued by the Company upon the Principal/Applicant's request and the analysis contained therein reflects the Company's findings on the sample(s) submitted by Principal/Applicant and/or sample(s) drawn by the Company at the time and place of performing the inspection/testing only. Company shall not be liable for any changes to the results herein due to effects of weather, transport, storage or other factors outside Company's control. Furthermore, the Company shall not be responsible to any parties on any business, financial and/or legal consequences for any transaction by using this report/analysis. Any unauthorised alteration or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. This document cannot be reproduced except in full, without prior approval of the Company.

Please note that this Report is issued under the following terms:

1. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that PT. CARSURIN approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that PT. CARSURIN in any way "guarantees" the letter performance of the product/equipment. Unless otherwise stated in this report, no test were conducted to determine long term effects of using the specific product/equipment.
2. The sample/s mentioned in this report is/are submitted or supplied by client.
3. Nothing in this report shall be interpreted to mean that PT. CARSURIN has verified or ascertained endorsement or marks from any other authority or bodies that August be found on that sample.
4. This report shall not be reproduced wholly or in parts and no reference shall be made by the client PT. CARSURIN in any advertisements or sales promotion
5. Unless otherwise stated, the tests were carried out in PT. CARSURIN Jl. Gaharu 1 Blok F2 No. 10 J, Multi Guna Niaga, Delta Silikon 3 Lippo Cikarang Bekasi



This report is made and issued by the Company upon the Principal/Applicant's request and the analysis contained therein reflects the Company's findings on the sample(s) submitted by Principal/Applicant and/or sample(s) drawn by the Company at the time and place of performing the inspection/testing only. Company shall not be liable for any changes to the results herein due to effects of weather, transport, storage or other factors outside Company's control. Furthermore, the Company shall not be responsible to any parties on any business, financial and/or legal consequences for any transaction by using this report/analysis. Any unauthorised alteration or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. This document cannot be reproduced except in full, without prior approval of the Company.

REPORT OF ANALYSIS

Description : Coconut Shell Charcoal Briquette for Barbeque
Manufactured / Shipper : PT. Pandu Green Energi
Bellezza BSA 1st Floor SA1-06,
Jl. Letjen Soep Grogol Utara, Kebayoran Lama,
Kota ADM, Jakarta Selatan, DKI Jakarta

Sample Weight : 3.00 Kgs
Date of Received Sample : August 23th, 2022
Date of Analysis : August 25th, 2022

Analysis

Analysis were performed at PT Carsurin Cikarang Laboratory (accreditation by KAN / National Accreditation Committee – Indonesia for ISO 17025:2017 Cert No. LP-415-IDN) in accordance with ASTM Standard.

The results of our analysis are as follows:

Parameter	Unit	Results		Method
		Wet Basic	Dry Basic	
Moisture	Pct	5.95	-	ASTM D1762-84 (REAPPROVED 2021)
Ash Content	Pct	14.00	14.89	ASTM D1762-84 (REAPPROVED 2021)
Volatile Matter	Pct	18.78	19.97	ASTM D1762-84 (REAPPROVED 2021)
Fixed Carbon	Pct	61.27	65.14	By Calculation

This certificate refers solely to the analysis in accordance with the details described herein and does not certify any other matter, and is issued without prejudice.

Jakarta, August 31st, 2022
PT. CARSURIN



CARSURIN
1968

Dede Jemmi Supriadi

Head of Laboratory

For verification of authenticity certificate or report, please e-mail to Charcoal@carsurin.com

The below findings are based on sample/s only, which is/are submitted or supplied by client. This report is valid within 90 days from the date of analysis.

This report is made and issued by the Company upon the Principal/Applicant's request and the analysis contained therein reflects the Company's findings on the sample(s) submitted by Principal/Applicant and/or sample(s) drawn by the Company at the time and place of performing the inspection/testing only. Company shall not be liable for any changes to the results herein due to effects of weather, transport, storage or other factors outside Company's control. Furthermore, the Company shall not be responsible to any parties on any business, financial and/or legal consequences for any transaction by using this report/analysis. Any unauthorised alteration or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. This document cannot be reproduced except in full, without prior approval of the Company.

